

DATA SHEET FOR AT275

POLYMER CELLULAR PVC FOAM
COLOUR: BLACK / WHITE
DESITY: 200KGS / M3

DESCRIPTION	RESULT <u>N</u>
Resistance to deformation under Compression (DIN 53576/B)	
Crushing on initial thickness of 25%	69,7
Crushing on initial thickness of 40%	109,7
Crushing on initial thickness of 65%	301,0
Residual deformation after Compression (DIN 53572)	
Room temperature, crushing 50%, 72 hours	
Residual deformation after 3 hours	7,9
Residual deformation after 4 hours	3,1
Residual deformation after 24 hours	1,1
Dimensional stability after heat treatment	
4h at 60° C (Longitu.dir)	1,0
4h at 60° C (Transver.dir)	0,1
4h at -30° C (Longitu.dir)	0,6
4h at -30° C (Transver.dir)	0,6

This information is given to the best of our knowledge. All test data are average values and should be considered as guidelines only.

DATA SHEET FOR A18 SELF ADHESIVE

<u>Construction Adhesive</u>	Permanent high tack solvent acrylic with excellent Ultraviolet and plasticiser resistance.
<u>Carrier</u>	Thin white hand tearable tissue.
<u>Liner</u>	White moisture stable.
<u>Thickness</u>	0.09m/m
<u>Tensile strength</u>	1 kg/cm
<u>Elongation</u>	3%
<u>Adhesion</u>	.45kg/cm
<u>Service Temp.</u>	-10° to +120°C
<u>Shelf Life</u>	12 months

This information is given to the best of our knowledge. All test data are average values and should be considered as guidelines only.